

For trade enquiries, please contact

Head - Petrochemicals

Mr. A S Sahney

Executive Director (Petrochemicals)
Phone: 91-11-26518230
E-mail: sahnayas@indianoil.in

Polymers Marketing

Mr. Raghunandhan .A.V

Chief General Manager (PCM)
Phone: 91-11-26518229
E-mail: avraghunandhan@indianoil.in

PX/PTA/Glycols Marketing

Mr. Subodh Goel

Chief General Manager (PCM)
Phone: 91-11-26524731
E-mail: subodhgoel@indianoil.in

LAB & Butadiene Marketing

Mr. S.P Selvam

Chief General Manager (PCM)
Phone: 91-11-26852702
E-mail: selvamsp@indianoil.in

Strategy & Projects

Mr. S.K Papneja

Chief General Manager (PCM)
Phone: 91-11-71725013
E-mail: papnejask@indianoil.in

Operations & Logistics

Mr. Saurabh Dutt

Chief General Manager (PCMO)
Phone: 91-11-26531047
E-mail: saurabhdutt@indianoil.in

Technical Services & PADC

Mr. Sumit Basu

Chief General Manager (PC)
Phone: 91-11-26531082
E-mail: bsumit@indianoil.in

Exports & Pricing

Mr. Nikhil Kalani

Chief Manager (PCM)
Phone: 91-11-26524739
E-mail: nkalani@indianoil.in

Sales Zone

North Zone-Delhi

Mr. Manoj Jha

General Manager
(Petrochemicals Sales)
10th Floor, SCOPE Minar, Core -2
District Centre, Laxmi Nagar
New Delhi-110092
Phone: 91-11-22448081
E-mail: mkjha@indianoil.in

North West Zone-Indore

Mr. Prashant Kumar

Chief Manager
(Petrochemicals Sales)
Indian Oil Bhawan, Plot No-8
Scheme No- 159,
Kasturba Thakre Marg,
MR -10, Indore -452016
Phone: 91-731-2970518
E-mail: prashantkumar@indianoil.in

East Zone-Kolkata

Mr. Kabisekhar Laha

Deputy General Manager
(Petrochemicals Sales)
9th Floor, BD Eastern Zone
IBP House, 34A Nirmal Chandra
Street, Kolkata-700013
Phone: 91-33-22150049
E-mail: klaha@indianoil.in

West Zone I-Mumbai

Mr. Sandeep Khanna

General Manager
(Petrochemicals Sales)
1st Floor, Sarjan Plaza,100,
Dr. Annie Besant Road, Worli
Mumbai -400018
Phone: 91-22-26524736
E-mail: ksandeep@indianoil.in

West Zone II-Ahmedabad

Mr. Amit Garg

Chief Manager
(Petrochemicals Sales)
4th Floor, Ashoka Chambers,
A -Wing, Rasala Marg, Mithakhali,
Ahmedabad-380006
Phone: 91-79-2526767
E-mail: garga@indianoil.in

South Zone -Chennai

Mr. Anupam Mishra

Deputy General Manager
(Petrochemicals Sales)
Indian Oil Bhawan, 139
Nungambakkam High Road
Chennai -600034
Phone: 91-44-28339248
E-mail: manupam@indianoil.in

For more information, please visit: www.iocl.com | <https://propel.indianoil.in>



Petrochemicals: World-scale Plants, World-class Technologies

IndianOil is one of the largest players in the domestic Petrochemicals market, offering a full slate of Petrochemical products and intermediates under the brand name *PROPEL*. The Corporation made its big-ticket entry into Petrochemicals with the commissioning of the country's largest LAB (Linear Alkyl Benzene, used in the production of detergents) plant at its Koyali Refinery in August 2004. An integrated PX/PTA (Paraxylene/Purified Terephthalic Acid) complex came up at Panipat in Haryana in 2006 with a world-scale capacity of 553 KTA. A world-class Naphtha Cracker of 857 KTA Ethylene capacity with downstream polymer units, set up at Panipat in 2010, is the largest operating Naptha cracker capacity in India. Its downstream unit produce about 52 grades of polymers catering to diverse range of applications.

Brief details of Polymer plants are given below:

Unit	Technology & Licensor	Capacity (KTA)
Polypropylene	Spheripol II – LyondellBasell, Italy	600 (2X300) at Panipat 680 (2X340) at Paradip
Dedicated HDPE	Hostalen – LyondellBasell, Germany	300 at Panipat
LLDPE/HDPE Swing	Sclairtech- Nova Chemicals, Canada	350 at Panipat

IndianOil has already implemented Petrochemical projects worth ₹24,000 crore. Further plans are on the anvil for various petrochemicals projects touching capex of ₹25,000 crore. As part of this mega plan, IndianOil has commissioned a Polypropylene plant with a capacity of 680 KTA at its Paradip Refinery in February 2019. A 356 KTA Ethylene Glycol plant would be commissioned at Paradip, Odisha in 2022. Further to the plan study is underway for PTA plant at Paradip.



Delivering Excellence, Propelling India's Progress

IndianOil – The Energy of India

Indian Oil Corporation (IndianOil) is India's largest commercial enterprise, with sales turnover of ₹5,14,890 crore and profits of ₹21,836 crore for the year 2020-21. It is also the leading Indian corporate in *Fortune's* prestigious 'Global 500' listing of the world's largest corporates, ranked at the 212th position for the year 2020.

As India's flagship national oil company, IndianOil's business interests straddle the entire hydrocarbon value-chain – from refining, pipeline transportation and marketing of petroleum products to exploration & production of crude oil & gas, marketing of natural gas and petrochemicals, besides forays into alternative energy and globalisation of downstream operations.



LLDPE / HDPE Grade Slate : Sclairtech Swing Plant

Product	Sector	Grade	MFI(L ₂)	Density	Special Characteristics	Application
LLDPE	LL FILM	010F18S	0.9	0.918	Good processability, Low gel, Good mechanical properties, Excellent optical properties. Contains slip and antiblock.	Liquid packaging film, Multilayer film for adhesive lamination, Carrier bags.
		010F18A	0.9	0.918	Good processability, Good mechanical properties, does not contain slip and antiblock.	Multilayer film for adhesive lamination, Mulch Film, Stretch Cling film.
		020F18A	2.0	0.918	Easy processability, Low gel, does not contain slip & antiblock.	Cast film for stretch wrapping, stretch cling film.
	DRIP LATERAL	010L22S	1.1	0.922	Excellent processability, Good strength, Controlled morphology, Low gel content.	Drip lateral pipe.
LLDPE	ROTATIONAL MOULDING	042R35A	4.5	0.935	Very good processability, Ease in de-moulding, Good mechanical strength.	Overhead water tanks, Loft tanks, Septic tanks, Toys, Garden furniture.
		040R40A	4.0	0.940	Superior Mechanical Strength, Excellent rigidity, Impact resistance and easy processability.	Medium and large tanks, Septic tanks, Manholes and Chambers.
LLDPE	INJECTION MOULDING	500M24A	50	0.924	Very good flow and processability.	Carrier resin for master batches, Injection moulding of flat and large warpage-free products and lids.
LLDPE	EXTRUSION COATING	065E24A	6.5	0.924	Good processability. Low neck-in, Good adhesion on substrates.	Extrusion coating on HDPE Raffia fabric, Paper etc. Base resin for XLPE compounds.
HDPE	INJECTION / COMPRESSION MOULDING	020M52	2.7	0.952	Superior Processability, Superior Mechanical properties.	Compression molded Caps and Closures.
		080M60	8	0.960	Good processability, Superior mechanical properties.	Crates for vegetables, milk, fish and material handling, Injection moulded Pallets, Caps & Closures.
	080M55	8	0.955	Good processability, Superior mechanical properties.	Caps & Closures.	
	080M60U	8	0.960	UV stabilised, Good processability, Superior mechanical properties.	Soft drink crates, Industrial crates for outdoor usage, Injection moulded Pallets, Caps & Closures.	
	180M50	20	0.950	Excellent flow properties, very good processability, DMF approved.	Injection Molded Housewares, Thin wall injection moulded products.	
HDPE	RAFFIA	010E52	0.9	0.952	Excellent orientation characteristics, Low water carry over, Excellent mechanical properties.	Woven sacks for fertilizer packaging, Wrapping fabric, Tarpaulin, Agri shade net, Raschel bags, Extruded sheets.
		012E50	1.2	0.950	Narrow MWD, Excellent orientation characteristics, Low water carry over. Superior mechanical properties.	Tarpaulin, Wrapping fabrics, Monofilaments for mosquito nets, fishing nets, etc.

HDPE and HMHDPE Grade Slate : Dedicated (Hostalen) Plant

Sector	Grade	MFI(L ₂)	Density	Special Characteristics	Application
HM Film	002DF50	0.22	0.950	Bimodal grade with very good processability with high molecular weight. Excellent dart impact strength.	Shopping bags, Films for wrapping, Liners.
GPBM	012DB54	1.3	0.954	Bimodal grade with very good processability, Good balance of stiffness, ESCR and impact properties. DMF approved.	Blow molded containers for lubricating oil packaging upto 5L capacity, Pharmaceutical edible oil & other general-purpose packaging, DWC pipe.
High ESCR Blow Molding	010DB50	1.2	0.950	Bimodal grade with very good processability, Superior mechanical properties, High ESCR properties.	High ESCR Blow molded containers, Containers for packing chemicals, pesticides, etc.
High Stiffness Blow Molding	012DB60	1.3	0.960	Superior Processability, Superior mechanical properties and impact resistance, High rigidity.	Containers and bottles up to 20 ltr capacities, Containers for packing Edible oils.
MBM	003DB52	0.40	0.952	Bimodal HMHD grade with very good processability, High stiffness, toughness & good ESCR properties.	Blow moulded containers upto 100 litres. DWC Pipe. Blow moulded water tanks, solar panels sloaters.
LBM	002DB52	0.20	0.953	Bimodal HMHD grade with good processability, Good balance of stiffness and impact properties.	Large Volume containers >100L for Chemicals, Pesticides, Lube Oils, Water etc.
PIPE	002DP48	0.25	0.950	Bimodal grade with good processability. Excellent impact & stiffness. Classified as MRS 10.0 material (PE-100) (Element certification).	Pipes for Water transportation, Sewerage, Industrial Piping etc.
	004DP44	0.45	0.950	Bimodal grade with very good processability, Classified as MRS 8.0 material (PE-80).	Pipes for Water transportation, Sewerage, Sprinkler pipes etc.
	010DP45	0.9	0.950	Bimodal grade with good processability. Classified as MRS 6.3 material (PE-63).	Pipes for Drip Irrigation and sprinkler applications, Pipes for drinking water, Industrial effluent etc.
	010DP45U	0.9	0.945	Bimodal grade with good processability, specially formulated for teleduct applications. It is UV stabilized grade. CACT approved for OFC ducts and telecom applications.	Teleducts for OFC, DWC pipes.

Polypropylene (PP) Grade Slate : Spheripol Plant

Family	Sector	Grade	MFI (L ₂)	Special Characteristics	Application	
HOMO POLYMER	INJECTING MOULDING	1030MG/P1030MG	3	Good balance of impact and rigidity, Good processability.	Industrial products, Household products, General purpose extrusion, Blending with Raffia.	
		1060MG/P1060MG	6	Good balance of impact and rigidity, Good processability.	Industrial products, Household products. Also used in blends in Thermoforming & Raffia.	
		1110MG/P1110MG	11	High flow and high rigidity, Very good gloss.	Rigid Packaging, Household articles, Furniture, Caps & Closures.	
		1110MAS/P1110MAS	11	A superior grade having high flow, very high stiffness with excellent gloss. The grade offers better productivity and reduces energy consumption. DMF approved.	Furniture, Household articles & Auto components where high stiffness is required.	
		1200MC	20	Good flow characteristics, high clarity, good processability. Bio-Compatibility approved.	Syringe barrel application, multicavity products, high clarity intricate products.	
		P1200MAS	20	High flow & high stiffness, Excellent gloss, Contains antistatic agent and faster molding cycles and	Housewares, Auto & Appliance component and Thin Wall & Multicavity Products.	
		P1500MG	40	High flow, good processability, Designed to offer faster molding cycles.	Housewares, Base resin for Compounds.	
	P1600MN	60	High flow, Excellent processability.	Thin walled injection Molding articles, compounding application		
	EXTRUSION COATING	1350EG/P1350EG	35	Excellent flow characteristics, Low neck-in & good processability, Good surface finish & excellent adhesion to substrate.	Extrusion coating on substrate PP Raffia fabrics, Lean blend with LDPE.	
		1030RG/P1030RG	3.5	Good processability, Low water carryover, Good balance of tenacity & elongation.	Woven sacks for Cement, Chemicals, Fertilizer, Food grain packaging, FIBC for bulk industrial packaging applications.	
	RAFFIA	P1045RG	4.5	High flow, good processability.	Tape for Wrapping fabric, tape for carpet backing application.	
		1030FG/P1030FG	3	Gel free, Good stretchability and processability.	General purpose & co-extruded BOPP film, Heat sealable films, Cast PP films, etc.	
	BOPP FILM	1100FS/P1100FS	10	Very good processability, Excellent gloss and clarity, contains Slip and Antiblock.	TQ films for packaging of snacks and bakery foods, Garment packaging, Textiles over wraps.	
	TQ FILM	P1030TC	3	Excellent processability and stretchability, High mechanical properties, High melt strength	Semi rigid thermoformed & vacuum formed articles, stationary sheets & packaging.	
	FIBER AND FILAMENT	1200YG/P1200YG	20	Good melt strength, stable extrusion even at high spinning speeds and stretch ratios.	Lower denier bulk continuous fibre, Continuous Fibre and Staple fibres, High tenacity continuous filament for straps, Low denier staple fibres for spun bond and non-woven.	
		P1250YG	25	Outstanding process stability and spinning behavior, High thermobonding properties.	Multifilament yarns, staple fibre and Non-woven, fine denier filament for carpet face yarn.	
		1350YG/P1350YG	35	High melt flow, High speed production of fine denier yarns, low gsm non-woven fabrics, Anti gas fading properties.	Spun bonded non-woven fabric for Disposables, Commodity packaging etc.	
	1350YH	35	High melt flow, Excellent Processability, soft feel non-woven fabrics, Anti gas fading properties	Spun bonded non-woven fabric for Medical disposables and Hygiene applications.		
	RANDOM CO-POLYMER	BLOW MOULDING	2020EC	2	Excellent clarity & gloss, superior processability & balance of stiffness & impact properties. DMF approved.	Blow moulded articles, sheet extrusion, IBM products.
		INJECTION MOULDING	2120MC	12	Excellent clarity & good processability, grade offers higher productivity and energy saving opportunities in processing. DMF approved.	Transparent injection moulded rigid containers, Houseware, Syringes, ISBM bottles.
2300MC			30	Excellent transparency, gloss, superior processability, balance in stiffness & impact properties.	Thin wall Injection Molding, High clarity Rigid containers, Housewares, ISBM products.	
IMPACT CO-POLYMER	INJECTION MOULDING	3030MG	3.5	Medium flow, Good stiffness and high impact strength balance.	Injection moulding of components for automobiles, Home appliances and Industrial products, Caps & Closures.	
		4015EG	1.5	Medium flow for easy processing, High impact strength & High stiffness.	Automotive components, Blow molded bottles, Sheets and Thermoforming.	
		4080MA	8	Medium flow for easy processing, Good impact & stiffness balance, anti-static properties.	Paint Pails, Furniture and industrial components.	
		4100MH	10	Medium flow, Very good processability, Long term heat ageing, Good impact & stiffness balance.	Battery containers, Industrial mouldings, Components requiring long heat exposure like under-the-hood automotive components.	
		5080MG	10	Good processability, No break (Superior impact strength).	Very High impact automotive components, Impact modifier in specialty PP compounds.	
		3120MA	12	Medium flow, Good processability, Good impact and stiffness balance, Anti-static properties.	Home appliances, Automotive components, PP compound for automotive components, Houseware, Molded furniture, Luggage shells.	
		3250MN	25	Good processability, Good surface finish & Gloss, Optimized balance of stiffness and toughness.	Appliance, Automotive Components & Housewares.	
		3400MN	40	High flow, Good processability, Low warpage, Nucleated grade.	Home appliances, PP Compound for automotive components, Thin wall Injection Moulding.	
		3650MN	65	High flow, Good processability, Low warpage, Nucleated grade.	PP Compounding for automotive components, TWIM, Appliances.	
	EXTRUSION COATING	3250MG	25	High flow, Very good processability, Low neck-in.	Extrusion coating on PP Raffia fabric, Sandwich Lamination of Raffia fabric with BOPP film or Craft Paper etc. in blends with suitable grades of LDPE.	

(*prefix 'P' before grade name denotes the Homo PP grades being produced from Paradeep Plant)